



# Eco-Coating White 55-40

**COLOR**

White

**WEIGHT PER GALLON**

11.5 lbs. (1.4 Kilo/Liter)

**AVERAGE NONVOLATILE**

60% by weight

50% by volume

**COVERAGE**

4 to 6 gallons per 100 sq.ft.(1.6 to 2.4 Liters/m<sup>2</sup>)

Dependent on the surface being covered.

**DRYING TIME**

Touch: 6 Hours

Through: 48 Hours

The drying time depends on temperature, humidity and film thickness.

**WATER VAPOR PERMEANCE (ASTM E96)**

.08 Perms at .040 dry film thickness (1 mm)

.05 Perms at .060 dry film thickness (1.5mm)

**SERVICE TEMPERATURE**

-20°F to 190°F (-29°C to 88°C)

**SAFETY**

Wet: Non-Flammable

Dry: See U.L. Classification

**CAUTION**

Although this product is water based and considered non-hazardous, good handling practices should be observed. Use with adequate ventilation. Avoid prolonged or repeated breathing of vapor. Avoid prolonged or repeated contact with skin. Do not take internally. In an emergency, call a physician. Keep out of reach of children.

**LIMITATIONS**

Do not freeze. Apply between 40°F (4° C) and 110° F (38°C). Caution: some foam insulations may warp if coated with water based coatings. Always use a light color over foam insulations outdoors.

VOC= .14 lbs/gal or 16.4 grams/liter

**WARRANTY TERMS:** The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change notice. To be sure information is current call Mon-Eco Industries, Inc.

**Terms of Warranty:** Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. **WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE.** No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

**DESCRIPTION**

Eco-Coating White 55-40 is a water based, fire resistive, water vapor retarding coating. It is designed for use on both indoor and outdoor low temperature equipment. It applies easily and dries to a smooth, white flexible finish. This product is safe to use with polystyrene insulation.

**SPECIFICATION COMPLIANCE**

Meets the requirements of Military Specification Mil-C-19565C. Type II. U.S.C.G. No. 164.012/134/0

Do not apply to roof surfaces with less than 1" pitch per linear foot. Continuous immersion caused by constant ponding of water should be avoided.

**APPLICATION METHOD**

Brush or spray

**MATERIAL PREPARATION**

Do not thin. Stir well.

**APPLICATION**

This product is designed for industrial use only and should be applied by trained and qualified craftspeople. Be sure surfaces are clean. When coating equipment and piping apply a tack coat of 2 gallons per 100 sq.ft. (.81 Liter/m<sup>2</sup>). Imbed the reinforcing membrane into the wet tack coat. Apply a finish coat of 55-40 at a rate of 4 gal/100 sq.ft (1.6 Liter/m<sup>2</sup>) over the membrane. Completely coat the membrane.

**CLEAN UP**

Wet: Warm, soapy water. Dry: 44-10

**ASBESTOS FREE**

**UNDERWRITERS LABORATORIES, INC.®**  
**CLASSIFIED**  
**GENERAL PURPOSE COATING**  
**SURFACE BURNING CHARACTERISTICS**  
**54H4**

**R10069 Applied to Inorganic Reinforced Cement Board**

	<b>USC</b>	<b>CNC</b>
<b>Flame Spread</b>	<b>10</b>	<b>10</b>
<b>Smoke Developed</b>	<b>5</b>	<b>5</b>
<b>Number of Coats</b>	<b>1</b>	<b>1</b>
<b>Rate Per Coat</b>	<b>50 Ft.<sup>2</sup>/gal</b>	<b>1.2 m<sup>2</sup>/L</b>

**Flash point of finished coating (closed cup): No flash to boiling.**

10/07

**MON-ECO INDUSTRIES, INC.**

5 JOANNA COURT•EAST BRUNSWICK, NJ 08816  
(732) 257-7942 • 800-899-6326 • FAX (732) 257-6525

[www.mon-ecoindustries.com](http://www.mon-ecoindustries.com)

